

## **Cement Test Certificate**

Lot 242 Russell Road East, Munster WA 6166 PO Box 38, Hamilton Hill WA 6963 T: +61 8 9411 1000 F: +61 8 9411 1150 Type GP General Purpose Cement

Final

**Product Certified:** 

Reportable Pr	operty Tes	st Method	Requirements of AS3972	Result	
Minor Additional Constituents			Max 5 %	Nil	
Calcium Sulphate				<5 %	
Mineral Addition			Max 7.5 %	<7.5 %	
Ground Granulated Iron Blast-Furnace	Slag			Nil	
Clinker				>86.5 %	
Nominal Blend			Requirements	Result	
	Sample Date:	4/01/2021			
	Sample Code:	B07ed63			
	Produced At:		Cockburn Cement, Munster Plant, WA		
	Test Certificate Number:	210046			

Reportable Property	iest method	AS3972	nesur
3 Day Strength	AS2350.11	N/R	45.4 MPa
7 Day Strength	AS2350.11	Min 35.0 MPa	54.2 MPa
28 Day Strength	AS2350.11	Min 45.0 MPa	67.2 MPa
Initial Set Time	AS2350.4	Min 45 min	120 min
Final Set Time	AS2350.4	Max 360 min	180 min
Soundness	AS2350.5	Max 5 mm	1 mm
Sulfuric Anhydride content (SO <sub>3</sub> )	AS2350.2	Max 3.5 %	3.2 %
Chloride Ion	BH-TM-0507	Max 0.10 %	0.015 %
Other Properties			
SiO <sub>2</sub>	AS2350.2	N/R	19.1 %
Al <sub>2</sub> O <sub>3</sub>	AS2350.2	N/R	5.1 %
Fe <sub>2</sub> O <sub>3</sub>	AS2350.2	N/R	2.7 %
CaO	AS2350.2	N/R	63.3 %
MgO	AS2350.2	N/R	1.3 %
Na <sub>2</sub> O Equivalent	AS2350.2	N/R	0.6 %
Loss on Ignition	AS2350.2	N/R	3.7 %
Fineness Index	AS2350.8	N/R	415 m²/kg
Normal Consistency	AS2350.3	N/R	28.8 %

This document shall not be reproduced except in full.

## REMARKS

These test result apply specifically to the sample as received at the Adelaide Brighton Cement Birkenhead Laboratory (Accreditation number: 252), 62 Elder Rd Birkenhead SA 5015.

This despatch grab sample complies to the requirements of AS3972:2010, Type GP Cement. N/R = No Requirement



Accredited for compliance with ISO/IEC 17025 - Testing. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.

Marchite

**Approved Signatory** M. Wythe

Issue Date:

9/02/2021