

GENERAL PURPOSE CEMENT - MUNSTER

PRODUCT DESCRIPTION

Cockburn Cement produces General Purpose Cement, Type GP, conforming to Australian Standard AS 3972.

General Purpose Cement is manufactured to exacting standards at our Munster Works in Munster, Western Australia, for use in the construction and building industry and in domestic applications.

SUPPLY

General Purpose Cement is available in bulk from the Munster Works and the Customer Service Centres in regional areas.

SPECIFICATION

General Purpose Cement exceeds the minimum specification given in AS 3972. General Purpose Cement is manufactured under a third party certified manufacturing and supply quality assurance system to ISO 9001 (BSI Certification No FS 604665).

General Purpose Cement is produced from Portland cement clinker and gypsum, and may contain up to 7.5% mineral additions.

APPLICATIONS

General Purpose cement is ideal for use in structural concrete, mortars, renders, grouts and cement based products, and can also be used as a general binder in areas such as soil stabilisation.

Supplementary cementitious materials:

General Purpose Cement is compatible with Fly ash, Amorphous Silica, and Ground Granulated Blast Furnace Slag conforming to the relevant sections of AS 3582.

Admixtures for concrete:

General Purpose cement is compatible with concrete admixtures complying with AS 1478.

TYPICAL PROPERTIES

General Purpose Cement as its name suggests, is the traditional basic cement used in industry. It is normally used when the special properties of low heat of hydration (temperature rise), high sulfate resistance or high early strength are not required.

Typical Physical Properties

Test	Typical Values	AS 3972 Requirement
Fineness Index (m ² /kg) AS 2350.8		
	380 - 440	-
Setting Time (hr:min) AS 2350.4		
Initial	2:15	Min 0:45
Final	3:15	Max 6:00
Soundness (mm) AS 2350.5		
	< 3	max 5
Compressive Strength ISO-CEN mortar bars (MPa) AS 2350.11		
3 Day	37 - 47	-
7 Day	48 - 58	35
28 Day	61 - 71	45

Typical Chemical Properties

Test	Units	Max AS 3972	Typical Values
Sulphur Trioxide	%	3.5	3.2
Loss on Ignition	%	-	3.5 – 4.5
Chloride	%	0.1	0.02
Equivalent Alkalies	%	-	0.5
Hexavalent Chromium	mg/kg	-	Trace
Crystalline Silica	%	-	Trace
Components			
Portland Clinker	%	-	85 – 93
Gypsum	%	-	5 - 7
Mineral Addition	%	7.5	up to 7.5

HANDLING AND STORAGE

Transportation may be in bulk road or rail tankers or in paper bags. General Purpose Cement can be stored in concrete or steel silos and paper bags for up six months provided that protection against ingress of moisture is observed throughout the storage of the product.

SAFETY INFORMATION

For safety information refer to the Safety Data Sheet for General Purpose Cement.



GENERAL PURPOSE CEMENT - MUNSTER

CONTACT POINTS

For further information contact the Sales and Marketing Department at:

Cockburn Cement Ltd

ABN 50 008 673 470

Lot 242 Russell Road East

Munster WA 6166

Telephone: 08 9411 1111

Email: sales@cockburncement.com.au

Web Site: www.cockburncement.com.au

DISCLAIMER

While the information in this Product Data Sheet has been prepared in good faith, Cockburn Cement Limited does not warrant that the information is accurate, complete or up to date.

Each user of any information, or any product referred to, in this Product Data Sheet must:

- Determine whether the information or product is suitable for their purpose;
- Assess and control any risks associated with the information or product; and
- Obtain professional advice in relation to the use of the information or product.

Failure to do so may result in serious damage or injury.

To the extent permitted by law, Cockburn Cement Limited:

- Excludes all representations, warranties and guarantees in relation to any information in this Product Data Sheet; and
- Will not be liable for any direct, indirect, consequential, incidental, special or economic loss (including but not limited to any loss of actual or anticipated profits, revenue, savings, production, business, opportunity, access to markets, goodwill, reputation, publicity, or use) arising from any use of or reliance on any information in this Product Data Sheet.

The Cockburn Cement logo and Cockburn Cement are registered trade marks of Cockburn Cement Limited and its related entities.