

WHITE HIGH EARLY STRENGTH CEMENT

PRODUCT DESCRIPTION

Cockburn Cement produces White High Early Strength Cement conforming to AS 3972.

White is a Type HE cement. This product is manufactured to exacting standards at our Kwinana Works in Kwinana, Western Australia, for use in the precast, construction and building industry as well as in domestic applications.

SUPPLY

White High Early Strength Cement is available in bulk from the Kwinana Works.

SPECIFICATION

White High Early Strength Cement exceeds the minimum Type HE specification given in AS 3972 and is manufactured under a third party certified manufacturing and supply quality assurance system to ISO 9001 (BSI Certification No FS 604665).

White High Early Strength Cement is produced from Portland cement clinker and gypsum, and may contain up to 7.5% mineral additions.

APPLICATIONS

White High Early Strength Cement is versatile in its use and has numerous applications. For example, in-situ concrete, precast concrete, concrete masonry, paving blocks, concrete tiles, garden furniture, glass reinforced cement (GRC), mortar and wherever a light coloured finish is required. Off-white cements are also often used for architectural purposes.

White High Early Strength Cement has a high C_3A content and it should not be used in any situation where sulfate attack is likely.

Admixtures for concrete:

White High Early Strength cement is compatible with concrete admixtures complying with AS 1478.

TYPICAL PROPERTIES

Physical Properties

Test	Typical Values	AS 3972 Requirement
Fineness Index (m^2/kg) AS 2350.8		
	360 - 460	-
Setting Time (hr:min) AS 2350.4		
Initial	1:20	Min 0:45
Final	2:10	Max 6:00
Soundness (mm) AS 2350.5		
	< 3	max 5
Compressive Strength ISO-CEN mortar bars (MPa) AS 2350.11		
3 Day	30 - 45	25
7 Day	42 - 54	40
28 Day	50 - 62	-

Chemical Properties

Test	Units	Max AS 3972	Typical Values
Sulphur Trioxide	%	3.5	3.2
Loss on Ignition	%	-	3.6 - 5.7
Chloride	%	0.1	0.02
Equivalent Alkalies	%	-	0.5
Hexavalent Chromium	mg/kg	-	Trace
Crystalline Silica	%	-	Trace
Components			
Portland Clinker	%	-	85 - 93
Gypsum	%	-	5 - 7
Mineral Addition	%	7.5	up to 7.5

HANDLING AND STORAGE

Transportation may be in bulk road or rail tankers. White High Early Strength Cement can be stored in concrete or steel silos.

SAFETY INFORMATION

For safety information refer to the Safety Data Sheet for White High Early Strength Cement.



WHITE HIGH EARLY STRENGTH CEMENT

CONTACT POINTS

For further information contact the Sales and Marketing Department at:

Cockburn Cement Ltd
ABN 50 008 673 470
Lot 242 Russell Road East
Munster WA 6166

Telephone: 08 9411 1111

Email: sales@cockburncement.com.au

Web Site: www.cockburncement.com.au

DISCLAIMER

While the information in this Product Data Sheet has been prepared in good faith, Cockburn Cement Limited does not warrant that the information is accurate, complete or up to date.

Each user of any information, or any product referred to, in this Product Data Sheet must:

- Determine whether the information or product is suitable for their purpose;
- Assess and control any risks associated with the information or product; and
- Obtain professional advice in relation to the use of the information or product.

Failure to do so may result in serious damage or injury.

To the extent permitted by law, Cockburn Cement Limited:

- Excludes all representations, warranties and guarantees in relation to any information in this Product Data Sheet; and
- Will not be liable for any direct, indirect, consequential, incidental, special or economic loss (including but not limited to any loss of actual or anticipated profits, revenue, savings, production, business, opportunity, access to markets, goodwill, reputation, publicity, or use) arising from any use of or reliance on any information in this Product Data Sheet.

The Cockburn Cement logo and Cockburn Cement are registered trade marks of Cockburn Cement Limited and its related entities.